Email:info@katalor.com

Tel:0086-21-61182423

## EN10083-2: C50, C50E steel works/steel structures/steel machining parts

C50 / C50E is medium carbon steel with high strength steel. It is usually used in normalizing, quenching or tempering condition. C50 / C50E steel is used in the manufacture of mechanical products and spring pieces, such as forging gear, tie rod, roller, shaft, friction plate, agricultural spindle dig plowshares and heavy-duty spindle bearing, etc. C50 / C50E steel are also with high wear resistance property.

The chemical composition of EN10083-2: C50/ C50E steel:

C: 0.47-0.55, Si: 0.4, Mn: 0.6-0.9, P: 0.03, S: 0.035, Cr: 0.4, Mo: 0.1, Ni: 0.4 Mechannical Properties in quenching and tempering condition (room temperature):

C50/ C50E: diameter≤16mm or thickness≤8mm:

Tensile strength of b (MPa): 750-900

Yield strength  $\sigma$  s (MPa):  $\geq$ 520

Elongation  $\delta$  5 (%):  $\geq$  13

C50/ C50E: 16mm < diameter≤40mm or 8mm < thickness≤20mm:

Tensile strength ob (MPa): 700-850

Yield strength  $\sigma$  s (MPa):  $\geq$ 460

Elongation  $\delta$  5 (%):  $\geq$ 15

C50/ C50E: 40mm < diameter ≤ 100mm or 20mm < thickness ≤ 60mm:

Tensile strength ob (MPa): 650-800

Yield strength  $\sigma$  s (MPa):  $\geq$ 400

Elongation  $\delta$  5 (%):  $\geq$  16

Recommended temperature in heat treatment: Normalizing: 830℃,

Quenching: 830°C, tempering 600°C

Equivalent material: SAE J403 1050 steel, JIS G4051 S50C steel Delivery condition of C50/ C50E steel: heat treatment (Q+T, annealing, normalizing or high temperature tempering), without heat treatment. Based on positive and pragmatic attitude, efficient management system, and perfect after-sale service, Shanghai Katalor guarantees to provide you with the best C50, C50E steel plates, round bar or steel tube/pipe. With our strong machining service, we can process the C50 and C50E raw material into C50/C50E steel works, steel structures and steel machining parts. If you have any needs, please feel free to contact us. We can offer you the technical support according to your demand, and also will offer you best quality and service.

Email:info@katalor.com Tel:0086-21-61182423



**Shanghai Katalor Enterprises Co., Ltd** located in shanghai of china, is specialized in manufacturing and exporting steel and casting product. Based on the domestic rich product resources and professional research on international market, Katalor's ervice has already spread many countries in Europe, America, Southeast Asia, Middle East, South America, Africa, and so on.

## **Contact US:**

Phone: 0086-18317160019
TEL: 0086-21-61182423
Fax: 0086-21-61182425
E-mail: info@katalor.com
Skype: shanghai.katalor

Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao

Industrial Area, Pudong New District, Shanghai