GL Grade B shipbuilding steel plate

GL Grade B shipbuilding steel plate a kind of hot rolled general tensile strength steel. The GL shipbuilding steel plate have yield strength of 34,100 psi (235 MPa), and ultimate tensile strength of 58,000 - 75,500 psi (400-520 MPa). GL Grade B shipbuilding steel plate come 4 grades in ordinary-strength steel for shipbuilding and grade B is one of them.

GL Grade B shipbuilding steel plate Application:

GL Grade B shipbuilding steel plate can be used for ship repairing, the offshore oil drilling platform, the platform pipe joints and other components.GL Grade B shipbuilding steel plate are almost exclusively used in the Shipbuilding Industry for the construction of structural parts of ships, barges and marine equipment.

Rolling Size of GL Grade B shipbuilding steel plate

Thickness	1.2-40mm
Width	1220-4200mm
Length	5000- 18000mm

Notes: coil thickness ≤ 25mm

GL Grade B shipbuilding steel plate Chemical Composition Heat Analysis:

Element	GL Grade B Max %	Element	GL Grade B max %
С	0.21	Ni	-

Office Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial

Area, Pudong New District, Shanghai

Mn	0.80	Мо	-
Si	0.35	AI	-
S	0.035	Nb	-
Р	0.035	V	-
Cu	-	Ti	-
Cr	-	N	-

GL Grade B shipbuilding steel plate Mechanical Properties:


	lThickness	Yield Strength	Tensile Strength	Elongation	Impact Energy
Grade	(mm)	MPa (min)	MPa	% (min)	(KV J) (min)
					0 degree
GL Grade B	4-260	235	400-520	22	27J

If you need GL Grade B shipbuilding steel plate stock or GL Grade B shipbuilding steel plate machining service , you can contact with Katalor, we can make the GL Grade B shipbuilding steel plate quotation according to your demands .



Office Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial

Area, Pudong New District, Shanghai



specialized in manufacturing and exporting steel and casting product. Based on the domestic rich product resources and professional research on international market, Katalor's ervice has already spread many countries in Europe, America, Southeast Asia, Middle East, South America, Africa, and so on.

Contact US:

Phone: 0086-18317160019
TEL: 0086-21-61182423
Fax: 0086-21-61182425
F-mail: info@katalor.com

E-mail: info@katalor.com **Skype:** shanghai.katalor

Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial

Area, Pudong New District, Shanghai