ABS AH32 shipbuilding steel plate

The ABS AH32 shipbuilding steel plates have yield strength of 45,500 psi (315 MPa), and ultimate tensile strength of 64,000 - 85,000 psi (440-590 MPa). All the ABS AH32 shipbuilding steel plate offered by Katalor Industry can be certificated by American Bureau of Shipping (ABS).

The application of ABS AH32 shipbuilding steel plate

ABS AH32 shipbuilding steel plates are mainly used for making the hull of ship building and ship repairing, the offshore oil drilling platform, the platform pipe joints and other components.

ABS AH32 shipbuilding steel plate Chemical Composition

Grade	C %	Si %	Mn %	Р%	S %	V %	AL %	Cr %
ABS AH32	0.180	0.1-0.5	0.90-1.6	0.035	0.035	0.05-0.10	0.015	0.200
	Cu %	Mo %	Nb %	Ni %	Ti %			
	0.350	0.080	0.02-0.05	0.400	0.020			

ABS AH32 shipbuilding steel plate Mechanical Properties

Grade	Thickness(mm)	MinYield(Mpa)	Tensile(Mpa)	Elongation (%)		Min Impact Energy	
ABS AH32	8mm-50mm	Min 315Mpa	440-590Mpa	22%	-	34J	
	51mm-70mm	Min 315Mpa	440-590Mpa	22%	-	38J	
	71mm-100mm	Min 315Mpa	440-590Mpa	22%	-	46J	
The min impact energy is longitudinal energy							

The rolling size of ABS AH32 shipbuilding steel plate

Thickness	3-150mm		
Width	1220-4200mm		
Length	5000-18000mm		

Notes: coil thickness ≤ 25mm

ABS AH32 Shipbuilding steel plates also can be used for producing container and bulk cargo vessels as well as cruise ships, ferries and yachts. Katalor is one of the famouse supplier of ABS AH32 shipbuilding steel plate. Katalor can supply ABS AH32 shipbuilding steel plate with client's **Office Address**:Room 301,Unit 6,lane 2500,xiupu Road,Kangqiao Industrial

Area, Pudong New District, Shanghai



request.welcome to contact katalor if you are buyers of ABS AH32 shipbuilding steel plate.



specialized in manufacturing and exporting steel and casting product. Based on the domestic rich product resources and professional research on international market, Katalor's ervice has already spread many countries in Europe, America, Southeast Asia, Middle East, South America, Africa, and so on.

Contact US:

Phone: 0086-18317160019

TEL: 0086-21-61182423 **Fax:** 0086-21-61182425 **E-mail:** info@katalor.com **Skype:** shanghai.katalor

Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial

Area, Pudong New District, Shanghai

Office Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial

Area, Pudong New District, Shanghai