



NM500 wear-resistant steel plate

Katalor can supply NM500 wear-resistant steel plate. GBT 24186 NM500 wear-resistant steel plate has advantages of high wear resistance, good impact performance, good temperature resistance, good connection performance, etc. NM500 wear-resistant steel plate's quality can be guaranteed by our quality controlled staff.

NM500 Wear Resistant Steel Chemical composition

Heat No.	Grade	C	Si	Mn	P	S	Ni+Mo+Cr	others	CEQ
S21300161	NM500	0.29	0.31	0.99	0.011	0.003	< 2.5	micro	0.71
S21300160	NM500	0.28	0.32	0.97	0.009	0.003	< 2.5	micro	0.77

NM500 Wear Resistant Steel Mechanical Properties

Standard		Grade	Thick. / mm	Rm / MPa		A50/ %	Impact T/ °C	KV2 / J	Hardness /HBW
GB/T 24186-2009		NM500	≤70	—		—	—	—	≥470
Plate No.	Heat No.	Grade	Thick. / mm	Re / MPa	Rm / MPa	A50/ %	Impact T/ °C	KV2 / J	Hardness /HBW
T3111011010	S21300161	NM500	21	1355	1665	9.5	-20	47/53/46	499
Q3331271010	S21300160	NM500	51	1573	1665	13.5	-20	42/44/56	499

we promise we can offer you the qualified NM500 wear-resistant steel plate at the competitive price and rapid delivery time. We can produce as our customer's requirement. We keep many NM500 wear-resistant steel plate stock in our warehouse, So hereby, we sincerely hope you join us, let's join hands to make you be the No. 1 in your local NM500 wear-resistant steel platemarket.

Office Address:Room 301,Unit 6,lane 2500,xiupu Road,Kangqiao Industrial Area,Pudong New District,Shanghai



Shanghai Katalor Enterprises
ONCE BELIEVE, TRUST FOREVER!

Email: info@katalor.com



specialized in manufacturing and exporting steel and casting product. Based on the domestic rich product resources and professional research on international market, Katalor's service has already spread many countries in Europe, America, Southeast Asia, Middle East, South America, Africa, and so on.

Contact US:

Phone: 0086-18317160019

TEL: 0086-21-61182423

Fax: 0086-21-61182425

E-mail: info@katalor.com

Skype: shanghai.katalor

Address : Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial Area, Pudong New District, Shanghai

Office Address: Room 301, Unit 6, lane 2500, xiupu Road, Kangqiao Industrial Area, Pudong New District, Shanghai